

Fair-Rite P/N 2518121217Y3

Y Chip Bead Material Grade

Nominal Chemical Composition

Supporting notes:

1. P/N 2518121217Y3 consists of:
 - a core Y Chip Bead Material Grade
 - b Termination Plating SnNiAg
2. Moisture Sensitivity Level (MSL)= 1
3. Max Reflow Temp= 260 degC
4. Max Time at Max Reflow Temp= 40 sec
5. RoHS 6/6 Compliant Terminations/ Wire are backwards compatible with standard Soldering Processes
6. RoHS Conversion Date= 1/1/2005
7. RoHS Compliance Marking is Contained on Shipping Labels

			Wt of core (g)=	
<u>Ferrite -Compound</u>	<u>CAS Number</u>	<u>wt %</u>	0.072	
Fe2O3	1309-37-1	65	0.04680	Compound Weight (g) Breakdown of Y Chip Bead Material Grade
ZnO	1314-13-2	17	0.01224	
NiO	1313-99-1	9	0.00648	
CuO	1317-38-0	6	0.00432	
MnO	1344-43-0	3	0.00216	

			Wt of termination (g)=	
<u>Termination Plating - Elements</u>	<u>CAS Number</u>	<u>wt %</u>	0.018	
Sn	7440-31-5	14.3	0.002574	Element Weight (g) Breakdown of Pb- Free Termination Plating
Ni	7440-02-0	6.9	0.001242	
Ag	7440-22-4	78.8	0.014184	

Calculated Maximum Levels of RoHS Restricted Substances Present in Y Chip Bead Material Grade

			Wt of core (g)=	
<u>Impurity Substance</u>	<u>RoHS Threshold (ppm):</u>	<u>ppm</u>	0.072	
Cr+6	1000	0.00	0	RoHS Impurity Substance Weight (g) Breakdown of Y Chip Bead Material Grade
Cd	100	0.00	0	
Hg	1000	0.00	0	
Pb	1000	0.00	0	
PBB	1000	0.00	0	
PBDE	1000	0.00	0	