

Fair-Rite P/N **5943006421**

43 Material Grade

Nominal Chemical Composition

<u>Compound</u>	<u>CAS Number</u>	<u>wt %</u>	Wt of core (g)=	
			19.00	
Fe2O3	1309-37-1	65	12.35	Compound Weight (g) Breakdown of 43 Material
ZnO	1314-13-2	21	3.99	
NiO	1313-99-1	10	1.90	
CuO	1317-38-0	4	0.76	

Supporting notes:

- RoHS Conversion Date= 1/1/2005
 - core 43 Material Grade
 - coating Urethane
- RoHS Compliance Marking is Contained on Shipping Labels

URETHANE COATING

<u>Compound</u>	<u>CAS Number</u>	<u>wt %</u>	Wt of core (g)=	
			0.50	
Calcium Carbonate	471-34-1	49	0.2450	Component Weight (g) Breakdown of Thermo-set Plastic Coating
Titanium Dioxide	13463-67-7	17	0.0850	
Methyl n-Amyl Ketone	110-43-0	12	0.0600	
Methyl Isobutyl Ketone	108-10-1	3	0.0150	
Xylene	1330-20-7	2	0.0100	
Ethyl benzene	100-41-4	0.3	0.0015	
Quartz	14808-60-7	0.2	0.0010	
Misc.	--	16.5	0.0825	

Calculated Maximum Levels of RoHS Restricted Substances Present in 43 Material Grade

<u>Impurity Substance</u>	<u>RoHS Threshold (ppm)</u>	<u>ppm</u>	Wt of core (g)=	
			19.00	
Cr+6	1000	0.00	0	RoHS Impurity Substance Weight (g) Breakdown of 43 Material
Cd	100	6.10	0.0001159	
Hg	1000	0.10	0.0000019	
Pb	1000	11.00	0.000209	
PBB	1000	0.00	0	
PBDE	1000	0.00	0	
Bis(2-Ethylhexyl) phthalate (DEHP)	1000	0	0	
Benzyl butyl phthalate (BBP)	1000	0	0	
Dibutyl phthalate (DBP)	1000	0	0	
Diisobutyl phthalate (DIBP)	1000	0	0	